



USA:(561) 330-9300

www.phoscrete.com
STELLAR MATERIALS INCORPORATED

EU:+31 (10) 2460264

ENGLISH

Revision 10/2/2008 (Check www.phoscrete.com for updates.)

PHOSCRETE 601-P

Formerly PHOSCRETE V/O

Phoscrete Concretos use the patented Stellar Binder System™ for easy and accurate mixing, controlled setting, and higher strengths. Phoscrete resists freeze-thaw cycling, inhibits rusting, and chemically bonds to concretes for permanent repairs.

CHARACTERISTICS

- Alumina - Silica - Medium Weight - Fine Grain - Fast Setting - Fast Curing -

PACKAGING

Bag Weight*	36 lbs	16.3 kg
Jug Weight*	11 lbs	5.0 kg
Drum Weight*	500 lbs	226.8 kg
Unit Weight*	83 lbs	37.6 kg
Yield / Unit*	0.5 ft3	0.0152 m3
Units / Ton*	24.15 short	26.63 metric
Board Feet / Unit*	6.5 bd ft	
Unit Equivalent	2 bags and 1 jug	
Wet to Dry Ratio*	15% - 16.5%	
Liquid Activator	PHOSCRETE	
Bags Per Pallet	48	
Drums Per Dry Pallet	1	

COMPRESSIVE STRENGTH**

1 Hour	3000 psi	211 kg/cm2	21 N/mm2
1 Day	6000 psi	422 kg/cm2	41 N/mm2
28 Days	9000 psi	633 kg/cm2	62 N/mm2

PERMANENT LINEAR CHANGE**

On Set	-0.10%
--------	--------

TYPICAL CHEMICAL ANALYSIS (After 1500F (816C))**

Al2O3	58.43%
SiO2	28.25%
Fe2O3	0.74%
P2O5	4.74%
Other	7.84%
Total	100.00%

ABRASION RESISTANCE** (ASTM C-704)

At Ambient	Fair cc loss
------------	--------------

BULK DENSITY**

As Placed	154 lbs/ft3	2467 kg/m3
-----------	-------------	------------

SHEAR BOND STRENGTH**

	7875 psi	554 kg/cm2	54 N/mm2
--	----------	------------	----------

WATER ABSORPTION**

	6.5%
--	------

FLEXURE AT CURE**

	1000 psi	70 kg/cm2	7 N/mm2
--	----------	-----------	---------

*Measures are approximate and may vary. For mixing partial units, contact Stellar Materials for specific wet-to-dry ratios. See Installation Guide for more detailed information.

**Test data shown are based on averages subject to normal variation on individual tests, and therefore should not be assumed to be maximum or minimum specifications.

Due to the unique nature of the Stellar binder system, test procedures vary slightly from ASTM. Documentation of these variations is available upon request.