



PHOSCRETE FORMULA 1-HC [Horizontal/Castable]

TECHNICAL DATA GUIDE (Formerly Phoscrete HC)

Very Rapid Hardening MPC (Magnesium Phosphate Cement) concrete for full and partial depth horizontal and castable concrete repairs.

DESCRIPTION

PHOSCRETE FORMULA 1-HC (F1-HC) is a two-part cementitious concrete repair material composed of magnesium oxide, aluminosilicates, aggregates, and reinforcing fibers (Dry Mix), plus a liquid phosphate activator (Liquid Activator). PHOSCRETE F1-HC is very rapid hardening, and gains strength suitable to vehicular traffic in less than one hour at a wide range of ambient temperatures. F1-HC forms both a chemical and a mechanical bond to cured concrete and to itself. F1-HC meets ASTM C 928, Type R3.

PROVEN APPLICATIONS

- ▶ Full depth and partial depth concrete repairs
- ▶ Interior and exterior concrete installation and repairs
- ▶ Horizontal surfaces: poured/castable applications
- ▶ Vertical and overhead surfaces: form and pour applications
- ▶ Bridge deck and parking deck repairs of reinforced concrete
- ▶ Highway concrete spall and rutting repairs
- ▶ Airport runway and apron concrete repairs
- ▶ Dowel bar retrofit, pre-cast joint grouting, bearing locations
- ▶ Freezer floors, industrial floors, and loading dock repairs
- ▶ Expansion joint nosing construction and repairs

ADVANTAGES

- ▶ Labor and time saving material: no sandblasting of steel bars, no anti-corrosion primer, no sacrificial anodes, sets fast.
- ▶ Easy and accurate mixing: two components, Mix in bucket one minute. No water, pre-extended mix. self-consolidating, easy clean up with water.
- ▶ Rapid return to service: exceeds 4,000 psi (28 MPa) compressive strength and 1,500 psi (10 MPa) bond strength 1 hour after placement at 68°F (20°C).
- ▶ Durable and hydrophobic: exceptional freeze-thaw and salt scaling resistance, even when exposed to MgCl₂ and CaCl₂.
- ▶ Fiber reinforced: high flexural strength and ductility.
- ▶ Strong mechanical and chemical bond to clean cured concrete and to itself with no cold joints.
- ▶ Stops rust and inhibits corrosion: converts iron oxide to metal phosphate.
- ▶ Does not out-gas after cure: accepts sealers and polymer coatings as soon as 15 minutes following initial set.
- ▶ Chemically stable: no added chlorides, resists chloride penetration.
- ▶ Not a vapor barrier; allows on grade applications.
- ▶ Environmentally friendly: no odor, no free silica.
- ▶ All temperature use – sets in temperatures cold as -5°F (-20°C)
-use Phoscrete Fast-Set/Slow-Set Admixture to manage setting/working time.

Packaging

Full Kit: [1] bag + [1] jug

Dry Mix bag: 55 lb. (25 kg)
polyethylene-lined paper bag

Liquid Activator jug:

10.4 lb. (4.7 kg) HDPE plastic jug

Kit Yield: 0.45 ft³ (0.0129 m³)

48 kits per full pallet.

Small Pail: 12.8 lb. (5.8 kg)

HDPE pail contains Dry Mix paper bag and HDPE Liquid Activator jar.

Small Pail Yield: 1.0 bf

(144 in³, 0.0024 m³)

Patch Kit tub: 0.8 lb. (0.4 kg)

HDPE Patch Kit tub contains plastic Dry Mix zip bag HDPE Liquid Activator jar plus plastic mixing stick.

Patch Kit Yield: (8 in³, 131 mm³)

Mixing Ratio

Pre-extended mix. Do not extend with sand or aggregate.

Wet-To-Dry Ratio: 18.75%

Mix Entire Patch Kit: [1] jar + [1] bag

Mix Entire Small Pail: [1] jar + [1] bag

Mix Entire Full Kit: [1] jugs + [1] bag

Storage

Store in clean, dry conditions in unopened, original packaging.

Shelf Life

Dry Mix: 24 months

Liquid Activator: 12 months

(when properly stored)

VOC Content

0 g/L: Less exempt solvents



PHOSCRETE FORMULA 1-HC [Horizontal/Castable]

Fresh Properties					
Test	Specification	Description	Time	Typical Results	
Set Time	ASTM C191	Time of Setting by Vicat Needles	lab temp supercooled†	Initial 8 min 15 min	Final 10 min 19 min
Slump	ASTM C143	Slump of Hydraulic-Cement Concrete	0 5 15 min supercooled†	9.5 in (24cm)	8.7 in (22cm) 6.2 in (16cm)
Density	ASTM C387	Density (Unit Weight) of Concrete		141 lb/ft ³	2259 kg/m ³
Air Content	ASTM C231	Air Content by Pressure Method		5.7%	
Strength Properties					
Test	Specification	Description	Time	Typical Results	
				psi	MPa
Compressive Strength	ASTM C109	Compressive Strength of Hydraulic Cement Mortars Using 2-in. Cube Specimens	1 hour	5000	34.5
			1 day	9000	62.1
			28 days	11500	79.3
Flexural Strength	ASTM C78	Flexural Strength of Concrete Using Simple Beam with Third-Point Loading	1 day	500	3.4
			28 days	700	4.8
Bond Strength	ASTM C882	Bond Strength by Slant Shear: Phoscrete - Concrete	1 hour	1500	10.3
			1 day	2500	17.2
			28 days	3000	20.7
		Bond Strength by Slant Shear: Phoscrete - Phoscrete	1 hour	1750	12.1
			1 day	2500	17.2
			28 days	3000	20.7
Tensile Strength	ASTM C496	Splitting Tensile Strength of Cylindrical Concrete Specimens	1 day	1000	6.9
			28 days	1200	8.3
Modulus of Elasticity	ASTM C469	Static Modulus of Elasticity and Poisson's Ratio of Concrete in Compression	28 days	3.1 E ⁺⁰⁶	21 E ⁺⁰⁶
				0.274	
Durability Properties					
Test	Specification	Description	Test	Typical Results	
Free Shrinkage	ASTM C157	Length Change of Hardened Concrete (Std)	28 Days Wet Dry	0.00%	-0.03%
Restrained Shrinkage	ASTM C1581	Age at Cracking and Induced Tensile Stress Characteristics under Restrained Shrinkage	180 Days Deformation	Did Not Crack	-60 µstrain
Freeze Thaw	ASTM C666-A	Resistance of Concrete to Rapid Freezing and Thawing in a Saturated Condition (300 cycles)	Durability Factor	94%	
Scaling	ASTM C672	Scaling Resistance of Concrete Surfaces Exposed to Deicing Chemicals (25 cycles) Results = Visual Material Loss lbs./ft ²	NaCl	0	0.00
			CaCl ₂	0	0.00
			MgCl ₂	0	0.00
Chlorides	ASTM C1202	Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration (Coulombs)	28 days	122 C (very low)	
	ASTM C1543	Penetration of Chloride Ion into Concrete by Ponding	90 days	10-20 mm	0.135%
			180 days	55-65 mm	0.117%
				10-20 mm	0.195%
Abrasion	California CT-550	Determining the Surface Abrasion Resistance of Concrete Specimens (mass loss)	24 hours	16 g	1.8%

All results were obtained at Lab temp of 68°F (20°C) with both components, Dry Mix and Liquid Activator, stored at Lab temp.

† Supercooled Liquid Activator at 17°F (-8°C)



GENERAL INSTALLATION GUIDELINES

- › Refer to [Phoscrete Formula 1 \[MALP Series\] Full Installation Guide](#), for the most complete documentation on best installation practices.
- › Refer to [Phoscrete Warm Temperature Guidelines](#) and [Phoscrete Cold Temperature Guidelines](#) for information on how to mix Phoscrete materials in warm (>70°F/20°C) and cold climates (<50°F/10°C), The Guidelines contain information about the use of Phoscrete Fast- and Slow-Set Admixtures, and best practices for cooling or supercooling the Liquid Activator. Cooling the Liquid Activator can be achieved on ice at 40°F (4°C), supercooling in a freezer at 10°F (-12°C). Liquid Activator's freezing point is -20°F (-29°C).
- › Refer to [Phoscrete Best Practices for Endure Admix Usage Chart](#) for details on working with Phoscrete Admixtures (ENDURE, Fast-Set, Slow-Set)

SURFACE PREPARATION

- › Concrete surface must be sound and fully cured.
- › Remove loose, damaged, and contaminated concrete.
- › Concrete profile should reach minimum CSP of 7-9 per ICRI Guidelines. Water-blasting is not recommended.
- › Repair area must not be less than 1-inch (2.5 cm) deep. >2-inch (>5 cm) depth is recommended. Saw-cut the edges of the repair area parallel and perpendicular to traffic to limit the number of load-bearing stress points.
- › Clean the surface of the area to be repaired from oil, grease, and other bond-inhibiting materials.
- › Surface must be frost-free, dry, and free of standing water. Use heat (torch) to eliminate surface moisture.
- › Remove loose scale (rust) from steel bars with a wire brush. Sandblasting is not required.
- › Replace reinforcing bars according to instructions from the designer. Generally, bars that lost 25% or more of their original diameter must be replaced.

PRIMER COAT

For challenging applications, where maximum bond strength is required, use Phoscrete Primer. Using a cooled Liquid Activator, apply a scrub coat of Phoscrete Primer to the prepared concrete substrate. Be sure to fill all voids. Complete the primer coat by placing a ¼ in. (1.5 cm) thin layer of Phoscrete Primer over the scrub coat, either wet or dry. Wait at least 15 minutes for Phoscrete Primer to set and bond prior to proceeding with PHOSCRETE F1-HC full repair installation.

MIXING

- › Mix PHOSCRETE F1-HC at the placement site.
- › The mix ratio is 18.75% Liquid Activator to Dry Mix. On-site measurement for partial unit mixing is not recommended. Inaccurate measurements will lead to poor material performance.
- › When mixing Full Kits, use a heavy-duty five [5] gallon bucket for mixing. Mix with a paddle (Phoscrete's urethane auger is highly recommended), using a dual or variable speed drill suitable for mixing (min. 7-amp, ½" chuck, side handle).
- › When mixing multiple Full Kits at once, use a paddle-style mortar mixer for placing large quantities (>2 cy) of Phoscrete.
- › When mixing Small Pails, use a minimum 18v variable speed drill on the high torque setting. Phoscrete's small urethane auger is highly recommended.
- › When mixing Patch Kit tubs, use the provided stirrer and mix by hand until the material is completely wetted out.
- › Pour the Liquid Activator in a clean bucket or the mortar mixer first. Next add admixtures (ENDURE and /or, Fast-Set or Slow-Set). Then add the Dry Mix into the bucket or mortar mixer, preferably while slowly running the mixer.
- › Mix for about 1 minute, until the material is fully wetted out and shows a uniform consistency. Do not over-mix.
- › A batch of Phoscrete MPC must be mixed, placed, and finished within 5 - 15 minutes depending on ambient temperature.

APPLICATION

- › Install immediately after mixing. Discard the batch if the material begins to setup in the pail or mixer.
- › Using a trowel or float, or with a gloved hand, scrub Phoscrete into the bottom and sides of the area to be repaired, being careful to fill all voids. Force the material against the edges of the repair.
- › Place Phoscrete level to the adjacent concrete surface. Screed off excess.
- › Finish Phoscrete using clean concrete floats and trowels. Magnesium floats work best. Tap on surface with trowel to bring liquid to the surface for best finish. Clean Phoscrete from trowels with a water-dampened cloth. Do not pour water on repair. Stop finishing once the surface of the placed material develops a "skin."
- › If the material finishes higher than the adjacent surface, use a diamond grinder to level surface as soon as 15 minutes following final set.



APPLICATION *(continued from page 3)*

- ▶ When multiple layers are applied, scarify the surface by scratching crisscross lines in the layer with a trowel prior to set for best adhesion. Phoscrete bonds to itself with no cold joints, whether wet or completely cured. If installing in lifts, do not apply a final layer thinner than 1-inch. (2.5 cm).
- ▶ If rain begins prior to final set, cover the surface with plastic sheeting for at least 15 minutes following initial set.
- ▶ On sloped surfaces, pour the material at the bottom of the slope and work your way up. Use a hand screed to move the material up the slope. When installing on steep inclines, use forms, or work in smaller increments (one kit at a time), and allow the material to set prior to the next pour.
- ▶ For expansion joint nosings, ensure that the hardened repair material is not higher than the approach slab. Use a grinding tool to cut a 45° bevel at the edge of the joint no sooner than 15 minutes after initial set. Standard compression or silicone seals can be applied immediately after grinding. Refer to Phoscrete's [Expansion Joint Installation and Repair](#).

CLEANING

- ▶ In-between batches, clean tools with water and wipe off excess water prior to contact with Phoscrete.
- ▶ When the job is completed, clean tools with water. Clean hands with soap and water.

LIMITATIONS

- ▶ Do not use any primer or admixtures other than those provided by Phoscrete.
- ▶ Do not extend PHOSCRETE F1-HC with aggregate. Do not add sand and/or any type of cement.
- ▶ Do not mix partial units unless accurately pre-measured.
- ▶ Minimum application thickness: 1-inch (2.5 cm), 2-inches (5 cm) recommended. Maximum application thickness: none
- ▶ Minimum ambient temperature: -5°F (-20°C)
- ▶ Do not use water when mixing, placing, or finishing PHOSCRETE F1-HC
- ▶ When wet, PHOSCRETE F1-HC cannot be placed in direct contact with galvanized steel (zinc).
- ▶ Proper application is the responsibility of the user. Field visits by Phoscrete personnel are for the purpose of making technical recommendations, not for supervising or providing quality control on the jobsite.

LIMITED WARRANTY NOTICE

Phoscrete Corporation (Phoscrete) warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, when used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond Phoscrete's control. PHOSCRETE MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of Phoscrete. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. PHOSCRETE WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND. Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Phoscrete's present knowledge and experience. However, Phoscrete assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third-party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Phoscrete reserves the right to make changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

HEALTH, SAFETY, AND ENVIRONMENTAL

Read, understand, and follow all Installation Instructions, Safety Data Sheets, and product label information for this product prior to use. The latest SDS can be obtained by visiting phoscrete.com, emailing your request to safety@phoscrete.com, or calling +1 561-420-0595. Use only as directed. For Hazardous Materials [or Dangerous Goods] Incident Spill, Leak, Fire, Exposure, or Accident, Call CHEMTREC® 24 Hours 800-424-9300 / +1 703-527-3887. Contracted by Phoscrete, CCN 866520.