



## PHOSCRETE FORMULA 3E-HC

### TECHNICAL DATA GUIDE

Rapid Hardening MKP (Magnesium Potassium Phosphate) concrete for overlays and repairs. Provides long-term durability for cold weather applications.

#### DESCRIPTION

PHOSCRETE FORMULA 3E-HC (F3E-HC) is a two-part cementitious concrete composed of magnesium oxide, potassium phosphate, aluminosilicates, aggregates, reinforcing fibers (Dry Mix) that must be mixed with water, plus a liquid soy-methyl-ester polystyrene (PHOSCRETE ENDURE™) admixture that is a concrete durability enhancer. PHOSCRETE F3E-HC is rapid hardening, and gains strength suitable to vehicular traffic in two hours at moderate ambient temperatures. PHOSCRETE F3E-HC forms both a chemical and a mechanical bond to cured concrete and to itself. PHOSCRETE F3E-HC meets ASTM C 928, Type R3.

#### PROVEN APPLICATIONS

- ▶ Fast-track bridge deck overlay with a minimum thickness ½ inch (1.25 cm)
- ▶ Full depth and partial depth concrete repairs
- ▶ Horizontal surfaces: poured/castable applications
- ▶ Pavement repairs, parking structures, marine structures.
- ▶ Airport runway and apron concrete repairs

#### ADVANTAGES

- ▶ Labor and time saving material: fast setting, self-consolidating, no sandblasting of steel bars, no anti-corrosion primer, no curing treatments, easy clean up with water.
- ▶ Easy and accurate mixing: two components plus water - Dry Mix in a pail and ENDURE in a bottle. Pre-extended mix.
- ▶ Can be pumped using bulk sacks and metered water for large volume pours and concrete pavement overlays.
- ▶ Rapid return to service: exceeds 2,500 psi (17 MPa) compressive strength and 1,500 psi (10 MPa) bond strength 2 hours following placement at 68°F (20°C). Ultimate strengths exceed 10,000 psi (69 MPa) compressive and 4,500 psi (31 MPa) bond.
- ▶ Durable and hydrophobic: exceptional freeze-thaw and salt scaling resistance, even when exposed to MgCl<sub>2</sub> and CaCl<sub>2</sub>.
- ▶ Fiber reinforced: high flexural strength and ductility.
- ▶ Strong mechanical and chemical bond to clean cured concrete and to itself with no cold joints.
- ▶ Stops rust and inhibits corrosion: converts iron oxide to metal phosphate.
- ▶ Chemically stable: no added chlorides, resists chloride penetration.
- ▶ Not a vapor barrier; allows on grade applications.
- ▶ Environmentally friendly: no odor, no free silica.
- ▶ All temperature use – heat/cool water and use Phoscrete Fast-Set/Slow-Set Admixtures to manage setting/working time.

#### Packaging

Bulk Sack 2200 lb. (1000 kg)

**Bulk Sack Yield:** 18 ft<sup>3</sup> - 0.66 yd<sup>3</sup>  
(0.509 m<sup>3</sup>)

Dry Mix Bag: 55 lb. (25 kg)

**Bag Yield:** 0.45 ft<sup>3</sup> (0.0129 m<sup>3</sup>)  
48 kits per full pallet.

ENDURE Jug: 100 fl. oz. (3 l)

Add 1% ENDURE by weight of dry mix. Use provided measuring cup to measure 8 oz. per [Admixture Chart](#).

ENDURE Jar: 8 oz. (236 ml)

Use 1 ENDURE jar per 55 lb. Dry Mix Bag.

Small Pail: 11 lb. (5 kg)

HDPE pail contains Dry Mix Bag, HDPE jar contains: Endure 1.6 oz (47 ml) and water 23 oz (677 ml)

**Small Pail Yield:** 1.0 bf  
(144 in<sup>3</sup>, 0.0024 m<sup>3</sup>)

#### Mixing Ratio

*Pre-extended mix. Do not extend with sand or aggregate.*

Water-To-Dry Mix Ratio: 13%

Measure 7.15 lbs water (110 fl. oz, 3.25l) per 55 lb. Dry Mix Bag.

Pre-measure water + 1% ENDURE Admix into clean plastic mixing bucket. Then add the entire pail of dry mix and mix thoroughly.

#### Storage

Store in clean, dry conditions in unopened, original packaging.

#### Shelf Life

**Dry Mix:** 24 months

**ENDURE:** 18 months

(when properly stored)

#### VOC Content

0 g/L: Less exempt solvents



LABORATORY TEST DATA

Fresh Properties					
Test	Specification	Description	Time	Independent Test Results	
Set Time	ASTM C191	Time of Setting by Vicat Needles	Initial   Final	18 min	22 min
Slump	ASTM C143	Slump of Hydraulic-Cement Concrete	5 min	9.0 in	
Density	ASTM C387	Density (Unit Weight) of Concrete		136 lb/ft <sup>3</sup>	2178 kg/m <sup>3</sup>
Air Content	ASTM C231	Air Content by Pressure Method		4.8%	
Strength Properties					
Test	Specification	Description	Time	Independent Test Results	
				psi	MPa
Compressive Strength	ASTM C109	Compressive Strength of Hydraulic Cement Mortars Using 2-in. Cube Specimens	2 hours	3500	24.1
			1 day	5000	34.5
			28 days	7000	48.2
Flexural Strength	ASTM C78	Flexural Strength of Concrete Using Simple Beam with Third-Point Loading	1 day	500	3.4
			28 days	600	4.1
Bond Strength	ASTM C882	Bond Strength by Slant Shear: Phoscrete - Concrete	2 hours	2000	13.8
			1 day	2400	16.5
			28 days	3000	20.5
Tensile	ASTM C496	Splitting Tensile Strength of Cylindrical Concrete	28 days	640	4.4
Modulus of	ASTM C469	Static Modulus of Elasticity	28 days	4.3 E <sup>+06</sup>	3.0 E <sup>+04</sup>
Durability Properties					
Test	Specification	Description	Test	Independent Test Results	
Free Shrinkage	ASTM C157	Length Change of Hardened Concrete (Std)	28 Days Wet   Dry	+0.14%	-0.14%
Freeze Thaw	ASTM C666-A	Resistance of Concrete to Rapid Freezing and Thawing in a Saturated Condition (300 cycles)	Durability Factor	95%	
Scaling	ASTM C672	Scaling Resistance of Concrete Surfaces Exposed to Deicing Chemicals (100 cycles) Results = Visual   Material Loss lbs./ft <sup>2</sup> (%)	NaCl	Visual 0	0.0 lbs/ft <sup>2</sup>
Chlorides	ASTM C1202	Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration (Coulombs)	28 days	1420 C	
	AASHTO T260	Chloride Content (%)	28 days Acid   Water	0.007%	0.002%
Abrasion	ASTM C779 Procedure B	Abrasion Resistance of Horizontal Concrete Surfaces	28 days	30 minutes	0.043 in
				60 minutes	0.060 in

\*Independent accredited laboratory test reports are available upon request.



## GENERAL INSTALLATION GUIDELINES

- Refer to [Phoscrete Formula 3 \[MKP Series\] Full Installation Guide](#), for the most complete documentation on best installation practices.
- Refer to [Phoscrete Best Practices for Endure Admix Usage Chart](#) for details on working with Phoscrete Admixtures (Endure, Fast-Set, Slow-Set).
- Cool water on ice below 40°F for additional flow during placement, and for additional working time when finishing.
- Warm water when working in cold temperatures for faster set.

## SURFACE PREPARATION

- Concrete surface must be sound and fully cured.
- Remove loose, damaged, and contaminated concrete, such as oil, grease, and other bond-inhibiting materials.
- Surface must be frost-free, dry, and free of standing water.
- Concrete profile should reach minimum CSP (Concrete Surface Profile) of 7-9 per ICRI Guidelines.
- Remove loose scale (rust) from steel bars with a wire brush. Sandblasting is not required.
- In case of repair applications, the repair area should not be less than 1-inch (2.5 cm) deep. >2-inch (>5 cm) minimum depth is recommended. Saw-cut the edges of the repair area parallel and perpendicular to traffic to limit the number of load-bearing stress points.

## MIXING

- Mix PHOSCRETE F3E-HC at the placement site.
- The mix ratio is 13% water to Dry Mix. On-site mixing of partial Dry Mix bags is not recommended. Inaccurate measurements will lead to poor material performance.
- When mixing bulk sacks, use a silo-style continuous mortar mixer for large volume applications.
- When mixing bags, use a heavy-duty five [5] gallon bucket for mixing. Mix with a paddle (Phoscrete's urethane auger is highly recommended), using a dual or variable speed drill suitable for mixing (min. 7-amp, ½" chuck, side handle).
- When mixing multiple bags at once, use a paddle-style mortar mixer for placing large quantities (>2 cy) of F3E-HC.
- When mixing Small Pails, use a minimum 18v variable speed drill on the high torque setting. For professional use, Phoscrete's small urethane auger is highly recommended.
- When mixing Patch Kit tubs, use the provided stirrer and mix by hand until the material is completely wetted out.
- Pre-measure and pour water into a clean bucket or mortar mixer first. Next add pre-measured ENDURE Admix liquid, and other Phoscrete admixtures (Fast-Set, Slow-Set) as needed. Then add Dry Mix into the bucket or drum, preferably while slowly running the mixer.
- Mix for about 1 minute, until the material is fully wetted out and shows a uniform consistency. Do not over-mix.

## APPLICATION

- A batch of Phoscrete must be mixed, placed, and finished within 15 - 25 minutes from mixing, temperature dependent.
- Phoscrete is thixotropic, so use vibration or tap with a trowel to increase flow.
- For concrete overlays:
  - Pour, place, and screed the material quickly to increase finishing time.
  - Finish F3E-HC by trowel, float, vibrating screed, or broom.
- For repair applications:
  - Scrub in a thin layer of F3E-HC into the bottom and sides of the area to be repaired, using a trowel, float, or a gloved hand, being careful to fill all voids.
  - Fill the repair in lifts using concrete floats and margin trowels. Force the material against the edges of the repair. In-between lifts, scarify the surface by scratching crisscross lines in the layer with a trowel prior to set for best adhesion bond. Phoscrete bonds to itself with no cold joints, whether wet or completely cured.
  - Finish the repaired area using clean concrete floats and trowels. Magnesium floats work best. Tap on surface with trowel to bring liquid to the surface for best finish. When installing in lifts, do not apply a final layer thinner than ½ inch (1.27 cm).
- Wipe Phoscrete from trowels with a water-dampened cloth. Do not pour water on repair.
- If the material finishes higher than the adjacent surface, use a diamond grinder to level surface as soon as 15 minutes following final set. Scarify or groove as necessary to insure adequate tire traction.
- If rain begins prior to final set, cover the surface with plastic sheeting for at least 15 minutes following initial set.
- On sloped surfaces, pour the material at the bottom of the slope and work your way up. Use a hand screed to move the material up the slope. When installing on steep inclines, use forms, or work in smaller increments (one kit at a time), and allow the material to set prior to the next pour.



## CLEANING

- › In-between batches, clean tools with a water dampened towel, and wipe off excess water prior to contact with Phoscrete.
- › When the job is completed, clean tools with water. Clean hands with soap and water.

## LIMITATIONS

- › Do not use any primer or admixtures other than those provided by Phoscrete.
- › Do not extend PHOSCRETE F3E-HC with aggregate. Do not add sand and/or any type of cement.
- › Do not mix partial units unless accurately pre-measured.
- › Minimum application thickness for overlays: ½-inch (1.25 cm),
- › Minimum recommended thickness for partial depth repairs: 2 inches (5 cm)
- › Maximum application thickness for full and partial depth repairs: none
- › Minimum ambient temperature: 35°F (2°C)
- › When wet, PHOSCRETE F3E-HC cannot be placed in direct contact with galvanized steel (zinc).
- › Proper application is the responsibility of the user. Field visits by Phoscrete personnel are for the purpose of making technical recommendations, not for supervising or providing quality control on the jobsite.

## LIMITED WARRANTY NOTICE

Phoscrete Corporation (Phoscrete) warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, when used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond Phoscrete's control. PHOSCRETE MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of Phoscrete. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. PHOSCRETE WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND. Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Phoscrete's present knowledge and experience. However, Phoscrete assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third-party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Phoscrete reserves the right to make changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

## HEALTH, SAFETY, AND ENVIRONMENTAL

Read, understand, and follow all Installation Instructions, Safety Data Sheets, and product label information for this product prior to use. The latest SDS can be obtained by visiting [phoscrete.com](http://phoscrete.com), emailing your request to [safety@phoscrete.com](mailto:safety@phoscrete.com), or calling +1 561-420-0595. Use only as directed. For Hazardous Materials [or Dangerous Goods] Incident Spill, Leak, Fire, Exposure, or Accident, Call CHEMTREC® 24 Hours 800-424-9300 / +1 703-527-3887. Contracted by Phoscrete, CCN 866520.